

Changzhou Sanzhong Welding Materials Co.,Ltd

www.asweld.com

	Т		www.aswei	u.com		
Standard: AWS E71T-11	Chemical Composition %					
	С	Mn	Si	S	P	Al
Grade E71T-11	≤ 0.30	≤ 1.75	≤ 0.60	≤ 0.03	≤ 0.03	≤ 1.80
Туре	Spool (MIG)					
Specification (MM)	0.8, 0.9, 1.0, 1.2, 1.6		Package S100/1kg S200/5kg S270,S300/15kg-20kg			
Mechanical Properties	Yield Strength (Mpa)		Tensile Strength (Mpa)		Elongation (%)	
	≥ 390		490 – 670		≥ 20	
MIG Welding	Diameter (MM)		1.0	1.2	1.6	
	Welding Current - A		60 – 180	80 – 220	110 – 270	
	Welding Voltage- V		12 – 20	13 – 22	14 – 26	
Performance characteristics	E71T-11 is self-shielded flux-cored wire with excellent welding performance and soft and stable arc. Small splash, easy slag removal, beautiful welding seam. Suitable for welding and welding, can all position of welding, the welding efficiency is high. The weld metal is treated with trace elements, and has good low - temperature toughness, good crack resistance and stable and reliable intrinsic quality.					
Application	The welding of structural parts of carbon steel and low alloy structural steel with tensile strength ≥ 490 MPA is the most widely used in the welding of important structures such as shipbuilding.					
Notice	 Welding workpiece should be done oil removal, rust removal treatment. Welding wire warehouse humidity should be maintained no more than 60%. Non-vacuum packaging wire storage time should not exceed half a year, vacuum packaging wire storage time should not exceed one year. 					

TEL:86 189 1234 9999 E-mail: manager@kkweld.com

D Whatsapp : +86 189 1234 9999